

VpCI® METALWORKING PRODUCTS

# VpCI®-379

## PRODUCT DESCRIPTION

VpCI-379 is a water-based corrosion preventive liquid concentrate designed to meet tough anti-pollution requirements. It is designed to protect ferrous and non-ferrous metals in sheltered areas, indoor or in packages not in direct exposure to rain and outdoor elements. VpCI-379 is designed as a complete replacement for oil-based preventives. The wide dilution range (between 5% and 50%) allows flexibility to customize the length of protection required versus applied cost per square foot (or m<sup>2</sup>). VpCI-379 is readily soluble and forms a clear solution in water. It is applied to metal surfaces by spraying or dipping. The protective coating is clear and will dry at ambient conditions to become dry-to-touch 30 minutes after application. VpCI-379 is can be removed with conventional alkaline cleaners, and can be coated over with paints and primers without removal.

## FEATURES

- Water-soluble
- Environmentally acceptable and safe to apply
- Superior protection against humidity
- Eliminates cleaning and housekeeping problems associated with oils
- Economical, can be diluted up to 1 part VpCI-379 to 20 parts water
- Forms clear and dry film which renders attractive appearance to protected parts
- Easy to remove, if necessary, or paintable with common coatings
- Displaces water from metal surfaces
- Unique vapor phase action also protects uncoated and difficult-to-reach areas
- NSN 8030-01-481-8928

## TYPICAL APPLICATIONS

- Castings forgings, tubular parts, machined, and honed metal components
- Gears, pumps, electric motors, housings, textile, and printing equipment
- Precision machined parts, structural steel, sintered metals, bars, and roll stock
- Additive to parts washers and rinse water systems, hydroblasting, and hydrotesting

Add VpCI-379 to water as follows for:

*Short term protection:*

1 part concentrate to 10-20 parts water

*Medium term protection:*

1 part concentrate to 6-10 parts water

*Protection up to 2 years:*

1 part concentrate to 1-5 parts water

If removal is necessary for subsequent operations such as plating, the usual preparatory operations of alkaline washing or degreasing easily removes the coating. In many operations, removal is not necessary since coatings, or paints can be applied directly over treated surfaces at dilutions over 1:5.

## TYPICAL PROPERTIES

Appearance	Clear amber liquid
pH	8.6-9.7 (Neat)
Non-volatile Content	28-35%
Density	8.5-8.8 lb/gal (1.01-1.05 kg/l)

## METALS PROTECTED


- Carbon steel
- Stainless steel
- Aluminum
- Cast iron
- Copper

## PACKAGING AND STORAGE

VpCI-379 is available in 5 gallon (19 liter) pails, 55 gallon (208) liter drums, liquid totes, and bulk. The product should be stored in a heated warehouse to avoid freezing. VpCI-379 has a shelf life of 12 months.



Refractometer Curve for VpCI-379



**FOR INDUSTRIAL USE ONLY**  
**KEEP OUT OF REACH OF CHILDREN**  
**KEEP CONTAINER TIGHTLY CLOSED**  
**NOT FOR INTERNAL CONSUMPTION**  
**CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION**

#### LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.

BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.

Distributed by:



4119 White Bear Parkway, St. Paul, MN 55110 USA  
Phone (651) 429-1100, Fax (651) 429-1122  
Toll Free (800) 4-CORTEC, E-mail [info@corotecvci.com](mailto:info@corotecvci.com)  
Internet <http://www.corotecvci.com>

printed on recycled paper  100% post consumer  
Revised 4/6/12. ©Cortec Corporation 1996-2012. All rights reserved. Supersedes: 8/14/07.  
© 2012, Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited.  
ISO accreditation applies to Cortec's processes only.